

G17

Niangon

SCIENTIFIC NAME
 Tarrietia utilis
LOCAL NAME
 Anguekong, Kwaeduma



Profile

The tree reaches a height of 32 to 43 m. The bole is straight and clear to 20 m in length, buttressed and sometimes irregular or stilt rooted in swampy areas. The trunk diameter attains 70 to 100 cm.

FAS Grade Sawn Hardwood Timber:

- FAS Grade Sawn Hardwood
- Air Dried / Kiln Dried
- Thickness=25/30/42/50/75/100/130mm
- Width=150mm up (10%)
- Length=2m up (5%)

Please Contact Us
with your specific
requirements
sales@silvaortus.com



Specification

| | | |
|---|--|--|
| Strength: Medium | Forest Availability: Average | Characteristics: Commercial redwood of durability and strength |
| Natural: Durability Moderate/High | Sawing: Moderate/Easy | Uses: veneer, vehicle bodies, plywood, joinery - exterior, furniture, frames, doors, boat construction |
| Shrinkage: Medium | Machining: Reportedly easy | Weight: Medium-Heavy 625kg/m3 at 12-15% moisture content. |
| Movement in Service: Medium | Finishing: n/a | |
| Forest Availability: Average | Fixing: n/a | |

