G11 Denya

SCIENTIFIC NAME

Cylicodiscus gabunensis

LOCAL NAME

Adoum, Edum, Okan

Profile

The sapwood is pinkish and very distinct from the heartwood which varies from yellow to brown with a greenish tinge: on exposure the colour becomes dark red-brown.

FAS Grade Sawn Hardwood Timber:

- FAS Grade Sawn Hardwood
- Air Dried / Kiln Dried
- Thickness=25/30/42/50/75/100/130mm
- Width=150mm up (10%)
- Length=2m up (5%)

Please Contact Us with your specific requirements
sales@silvaortus.com

Specification

Strength:
High

Natural:
Durability Very High

Shrinkage:
Large

Movement in Service:
n/a

Forest Availability:
Plentiful

Forest Availability:
Plentiful

Sawing:
Hard

Machining:
Hard

Finishing:
n/a

Fixing:
n/a

Characteristics:
Very high strength and durability for arduous applications

Uses:
flooring - heavy duty, ship and boat work, piling, bridges, sleepers, mining timbers, sea defence and dock work, construction - heavy

Weight:
Very Heavy 950kg/m3 at 12-15% moisture content.