GV 4

Ceiba

SCIENTIFIC NAME

Ceiba pentandra

LOCAL NAME

Doum, Enia, Fromager

Profile

Ceiba is very soft and light; density of air-dried wood is 320 kg/m3 (20 lb/ft3). In strength, the wood is comparable with basswood (Tilia americana). Ceiba dries rapidly without marked deterioration.

Decorative Veneers

Supply Specification:

- Thickness: 0.55mm to 1mm
- Width: 10cm and up
- Length Furniture: 2.10M
- Length Door: 2.10M - 2.45M
- Length Panel: 2.50M - 4.0M

Please Contact Us with your specific requirements
sales@silvaortus.com

Specification

Strength:
Low

Natural:
Durability Low

Shrinkage:
Small

Movement in Service:
n/a

Forest Availability:
Abundant

Forest Availability:
Abundant

Sawing:
Very Soft

Machining:
Blunting effect

Finishing:
n/a

Fixing:
n/a

Characteristics:
Very light and soft species for interior use

Uses:
boxes, food containers, mouldings, veneer for blockboard, veneer for plywood

Weight:
Light 300kg/m3 at 12-15% moisture content.